


























Product quality		
Formats		914 x 457 x 6,0 mm
Packaging	Pack:	5 elements / 2.088 m ² / 21.067 kg
	Pallet:	40 packs / 83,540 m ² / 882,66 kg

Tolerances (Requirement EN 16511:2023)		
Squareness of the elements (≤ 0.20mm)		≤ 0,15 mm
Determination of Linearity (≤ 0.30 mm/m)		≤ 0,20 mm/m
Flatness concave / convex	lengthwise (≤ 0.50/≤ 1.0 %)	≤ 0,30/≤ 0,50 %
	wide (≤ 0.15/≤ 0.20 %)	≤ 0,10/≤ 0,15 %
Surface flushness	(average ≤ 0.10 mm)	(average ≤ 0.10 mm)
	(max. ≤ 0.15 mm)	(max. ≤ 0.15 mm)
Opening between installed elements	(average ≤ 0.15 mm)	(average ≤ 0,05 mm)
	(max. ≤ 0.20 mm)	(max. ≤ 0.10 mm)

Guarantee (according Parador guarantee conditions)		Notes
Domestic area	Commercial area	- suitable for all-over adhesion (see notes in our advisor)
Lifetime	10 years	- cleaning an maintenance see instructions
		- technical changes reserved

Classification		
		
Utility class 23 = domestic areas with intensive use	Utility class 33 = commercial areas with intensive use	
The design floor meets all requirements of the designated utility class.		
Requirements / properties	Test method	Rating
 Wear layer	ISO 24340	0,55 mm
 Surface Coating		PUR
 Reaction to fire	EN 13501-1	B _f -s1
 Slip resistance	EN 13893 EN 14041	μ ≥ 0,30 DS
 Staining resistance	EN 438-2	Category 1 + 2: level 5, no visible change Category 3: level 4, slight change
 Light fastness	EN ISO 105 - B02	Blue wool scale: Stage ≥ 6
 Resistance to roller castor chairs	EN ISO 4918	Type W, no visible changes
 Thermal resistance Suitable for installation over underfloor heating when using an appropriate moisture barrier.	EN 12667	0,029 m ² *K/W
 Moving a furniture leg	EN ISO 16581	No visible damage (foot type 0)
 Indentation-residual	EN ISO 24343-1	≤ 0,10 mm
 Acoustical - Impact noise reduction	EN ISO 10140	17 dB
 Locking strength	ISO 24334	lengthwise ≥ 4 KN/m transversely ≥ 3 KN/m
 Abrasion	ISO 24338, Procedure B	> 5.000 rev.
 Dimensional stability	EN ISO 23999	≤ 0,20 %
 Water resistance	EN 317	waterproof
 Micro scratch resistance	EN 16094	Method A MSR-A1 For mat surfaces (gloss ≤ 7): ≤ 1,5 unit change at 60°
 Antimicrobial activity	ISO 22196	Antibacterial
 Slip resistance on an inclined plane	EN 16165, Annex B	Mineral texture: R9
 Disposal	EAK-Code-number	20 01 39

Changed:	QMB Parador	File:	PA_TDS_Designboden_Vinyl_Trendtime-5_EN_20231001
Date:	15.12.2018	Latest update at:	https://parador.de/en/services/downloads/design-flooring
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.10.2023