

| Product quality | | | | | | | |
|------------------|---------|---|----------------------------------|----------------------------------|--------------------------------|--|---------------------------------|
| Formats | | Trendtime 1 | Trendtime 2 | Trendtime 4 | Trendtime 5 | Trendtime 6 | Trendtime 8 |
| | | 1285 x 158 x 8 mm | 850 x 95 x 8 mm | 1285 x 400 x 8 mm | 638 x 330 x 8 mm | 2200 x 243 x 9 mm | 1285 x 330 x 8 mm |
| Packaging | Pack: | 10 Elements | 26 Elements | 5 Elements | 10 Elements | 5 Elements | 5 Elements |
| | | 2.03 m ² / 15.35 Kg | 2.1 m ² / 15.87 Kg | 2.57 m ² / 20.945 Kg | 2.105 m ² / 15.3 Kg | 2.673 m ² / 22.8 Kg | 2.12 m ² / 16.35 Kg |
| | Pallet: | 45 Pack | 30 Pack | 28 Pack | 40 Pack | 39 Pack | 34 Pack |
| | | 91.364 m ² / 705.71 Kg | 62.99 m ² / 491.17 Kg | 71.96 m ² / 586.46 Kg | 84.216 m ² / 627 Kg | 104.247 m ² / 889.2 Kg | 72.09 m ² / 570.9 Kg |
| Guarantee | | | | | Notes | - not ready for glue-down | |
| Domestic area: | | 25 Years (According Parador guarantee conditions) | | | | - cleaning an maintenance see intruction | |
| Commercial area: | | 5 Years (According Parador guarantee conditions) | | | | - technical changes reserved | |

| Product labeling | | | | | | | Tolerances (EN 13329) | | |
|------------------|--|--------------------|---|-----------------|-----------------|---|----------------------------------|---|------------------|
| | | | | | | | | Squarerness of elements (≤ 0,20 mm) | ≤ 0.10 mm |
| EN 14041 : 08 | Emissionsgeprüftes Bauprodukt nach DIN-Grundsätzen Z-156.606-453 | 100% emissionsfrei | Qualitäts-Zertifikat mit Sicherheit geprüfte Qualität | Prof.-Nr. 13301 | PEFC/04-31-0507 | THIRD-PARTY VERIFIED EPD ISO 14025 and EN 15804 | INSTITUT FÜR BAU UND UMWELT e.V. | Determining the straightness of the edges (≤ 0,30 mm/m) | ≤ 0.10 mm/m |
| | | | | | | | | Height differences of the elements (average ≤ 0.10 mm) | mittel ≤ 0.05 mm |
| | | | | | | | | (max. ≤ 0.15 mm) | max. ≤ 0.10 mm |
| | | | | | | | | Opening between installet elements (average ≤ 0.15 mm) | mittel ≤ 0.05 mm |
| | | | | | | | | (max. ≤ 0.20 mm) | max. ≤ 0.10 mm |
| | | | | | | | | Block alignment | ± 2 mm |

| Classification product features | | | | | | | |
|---------------------------------|--|------------------------------------|---|--|---|---|---------------------------------------|
| | | Test standard | Rating | | | Test standard | Rating |
| | Utility class 23 domestic areas with intensive use | EN 13329 | Living room, hall, kitchen, home office | | Slip resistance | EN 13893 EN 14041 | μ ≥ 0.35 DS |
| | Utility class 32 commercial areas with medium use | EN 13329 | Classrooms, small offices, shops | | Electrical behaviour | EN 1815 | < 2,0 kV antistatic ability |
| | Abrasion | EN 13329, Annex E | AC 4 (≥ 4.000 Umd.) | | Thermal conductivity Underfloor heating – suitable, with the backing material and vapor barrier | EN 12664 | 0.048 m ² *K/W |
| | Impact resistance | EN 13329, Annex F | IC 2 | | Effect of a furniture leg | EN 424 | No visible changes |
| | Reaction to fire | EN 13501-1 | C _f s1 | | Indentation-residual | EN 433 | No visible changes |
| | Staining resistance | EN 438-2 | Category 1 + 2: level 5 Category 3: level 4/5 | | Locking strength of mechanically assembled panels | ISO 24334 | - |
| | Cigarette resistance | EN 438-2 | level 4 | | Accoustical impact noise reduction | ISO 717-2 | 14 db (with Akustik-Protect 100) |
| | Light fastness | EN ISO 105 - B02 EN 20105 - A02 | Blue wool scale: Stage ≥ 6 Grey scale: Stage ≥ 4 | | Dimensional stability | ISO 24339 | - |
| | Resistance to roller castor chairs | EN 425 | No visible changes | | Surface soundness | EN 433 | ≥ 2.2 N/mm ² |
| | Formaldehyde (E1 = 0.1 ppm) | EN 717-1 | ≤ 0.05 ppm | | Slip resistance on an inclined plane | DIN 51130 | Depending on structure: -/R 9/R 10 |
| | Thickness swelling | EN 13329, Annex G (≤ 18 %) | ≤ 12 % | | Disposal | Privat waste disposal with normal household waste, bulky waste possible | |
| | Scratch resistance | EN 438 | Level 4 | | | | |

| | | | |
|--|------------|-------------|--|
| Changed: | QMB | File: | PA_TDS_Laminat_Trendtime_EN_2014 |
| Date: | 01.01.2014 | Updates at: | www.parador.de |
| Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from: | | | 01.03.2014 |