

Product quality		
Formats		1522 x 225 x 6 mm
Packaging	Pack:	6 elements / 2.055 m ² / 20.726 kg
	Pallet:	39 packs / 80.133 m ² / 853.31 kg

Tolerances (Requirement EN 16511:2023)		
Squareness of the elements ($\leq 0.20\text{mm}$)		$\leq 0,15\text{ mm}$
Determination of Linearity ($\leq 0.30\text{ mm/m}$)		$\leq 0,20\text{ mm/m}$
Flatness concave / convex	lengthwise ($\leq 0.50/\leq 1.0\%$)	$\leq 0,30/\leq 0,50\%$
	wide ($\leq 0.15/\leq 0.20\%$)	$\leq 0,10/\leq 0,15\%$
Surface flushness	(average $\leq 0.10\text{ mm}$)	(average $\leq 0.10\text{ mm}$)
	(max. $\leq 0.15\text{ mm}$)	(max. $\leq 0.15\text{ mm}$)
Opening between installed elements	(average $\leq 0.15\text{ mm}$)	(average $\leq 0,05\text{ mm}$)
	(max. $\leq 0.20\text{ mm}$)	(max. $\leq 0.10\text{ mm}$)

Guarantee (according Parador guarantee conditions)		Notes
Domestic area	Commercial area	- suitable for all-over adhesion (see notes in our advisor)
Lifetime	10 years	- cleaning an maintenance see instructions
		- technical changes reserved







Classification		
		
Utility class 23 = domestic areas with intensive use		Utility class 33 = commercial areas with intensive use
The design floor meets all requirements of the designated utility class.		
Requirements / properties	Test method	Rating
 Wear layer	ISO 24340	0,55 mm
 Surface Coating		PUR
 Reaction to fire	EN 13501-1	B _n -s1
 Slip resistance	EN 13893 EN 14041	$\mu \geq 0,30$ DS
 Staining resistance	EN 438-2	Category 1 + 2: level 5, no visible change Category 3: level 4, slight change
 Light fastness	EN ISO 105 - B02	Blue wool scale: Stage ≥ 6
 Resistance to roller castor chairs	EN ISO 4918	Type W, no visible changes
 Thermal resistance Suitable for installation over underfloor heating when using an appropriate moisture barrier.	EN 12667	0,029 m ² *K/W
 Moving a furniture leg	EN ISO 16581	No visible damage (foot type 0)
 Indentation-residual	EN ISO 24343-1	$\leq 0,10\text{ mm}$
 Acoustical - Impact noise reduction	EN ISO 10140	17 dB
 Locking strength	ISO 24334	lengthwise $\geq 4\text{ KN/m}$ transversely $\geq 3\text{ KN/m}$
 Abrasion	ISO 24338, Procedure B	$> 5.000\text{ rev.}$
 Dimensional stability	EN ISO 23999	$\leq 0,15\%$
Water resistance	EN 317	waterproof
Micro scratch resistance	EN 16094	Method A MSR-A1 For mat surfaces (gloss ≤ 7): $\leq 1,5\text{ unit change at }60^\circ$
Antimicrobial activity	ISO 22196	Antibacterial
Slip resistance	EN 16165, Annex B on an inclined plane	Authentic texture / vintage texture: R9 / Brushed texture / elegant texture / matt-finish texture / natural matt texture / natural texture: R10
	EN 16165, Annex C pendulum test	PTV (dry / wet) ≥ 36 Low slip potential according to UK Slip resistance group
Disposal	EAK-Code-number	20 01 39

Changed:	QMB Parador	File:	PA_TDS_Designboden_Vinyl_Trendtime-8_EN_20250101
Date:	15.12.2018	Latest update at:	https://parador.de/en/services/downloads/design-flooring
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.01.2025