PARADOR **Laminate Basic 600V**

Product quality		
Formats	1285 x 243 x 8mm	2200 x 243 x 8mm
Packaging	Pack: 7 elements / 2,186m² / 15,834 kg	Pack: 6 elements / 3,208m² / 22,38 kg
	Pallet: 42 packs / 91,80m² / 665 kg	Pallet: 39 packs / 125,09m² / 872 kg
Guarantee (according Parador guarantee conditions)		
Domestic area	15 years	
Commercial area	5 years	
Notes	- not suitable for all-over adhesion - cleaning an maintenance see instructions - technical changes reserved	

Tolerances (EN 13329)		
Squareness of the elements (≤ 0.50 mm)		≤ 0,10mm
Determination of Linearity (≤ 0.30 mm)		≤ 0,10 mm/m
Surface flushness	**(average ≤ 0.15 mm)**	(average ≤ 0.05 mm)
	(max. ≤ 0.15 mm)	(max. ≤ 0.10 mm)
Opening between installed elements	**(average ≤ 0.15 mm)**	(average ≤ 0.05 mm)
	(max. ≤ 0.20 mm)	(max. ≤ 0.10 mm)
Flatness of elements	**fw, concave ≤ 0,15 % fw, convex ≤ 0,20 %**	
	fl, concave ≤ 0,50 % fl, convex ≤ 1,00 %	

EN 14041:2004/AC:2006 · A+ · www.blauer-engel.de/uz176 · TESTED PRODUCT ID 1112 - 17656 - 001 · floor score · QNG READY · PEFC PEFC/04-31-0507 · EPD ISO 14025 and EN 15804

Classification

Utility class 23 = domestic areas with intensive use	Utility class 32 = commercial areas with medium use
The laminate flooring meets all requirements of the designated use class.	

Requirements / properties		Test method	Rating
	Abrasion	ISO 24338, procedure A	AC 4 (≥ 4.000 rev.)
	Impact resistance (small ball)	EN 17368	≥ 35mm
	Impact resistance (big ball)	EN 13329, Annex C	≥ 750mm
	Reaction to fire	EN 13501-1	C_{fl} s1
	Slip resistance	EN 13893	μ ≥ 0,35
		EN 14041	DS
	Staining resistance	EN 438-2	Category 1+2: level 5
			Category 3: level 4/5
	Cigarette resistance	EN 438-2	level 4
	Light fastness	EN ISO 4892-2	Grey scale: Stage ≥ 4
	Resistance to roller castor chairs	EN ISO 4918	Type W, no visible changes
	Thermal resistance Suitable for installation over underfloor heating when using an appropriate underlay and moisture barrier.	EN 12664	0,048 m²*K/W
	Moving a furniture leg	EN ISO 16581	Type 0, no visible changes
	Indentation-residual	ISO 24343-1	≤ 0,05mm
E1 HCHO	Formaldehyde emission (E1 = 0.1 ppm)	EN 16516	≤ 0,05 ppm
	Locking strength of mechanically assembled panels	ISO 24334	> 1 kN/m (long side)
			> 2 kN/m (short side)
	Acoustical - Impact noise reduction	ISO 717-2	18 dB (on Akustik-Protect 100)
	Dimensional changes after changes in relative humidity	EN 13329, Annex A	≤ 0,9mm
	Thickness swelling	ISO 24336 (≤ 18 %)	≤ 13 %
	Water resistance	ISO 4760	Requirements met (24h)
	Surface soundness	EN 13329, Annex B	≥ 1,8 N/mm²
	Scratch resistance	EN 438-2	Level 4
	Slip resistance on an inclined plane	EN 16165, Annex B on an inclined plane	Matt finish texture: R10 Natural texture / Natural matt texture: R9
		EN 16165, Annex C pendulum test	PTV (dry (slider 96)) ≥ 36 Low slip potential according to UK Slip resistance group
	Disposal		EAK-Code-number 20 01 38