

PARADOR

Engineered wood flooring Trendtime 10 „Chevron“

Product properties		Tolerance (EN 13489)	
Article #	1748482 / 1748483 / 1748484 / 17484486 / 1748487 / 1748490	Admissible difference in length	± 0.1 %
Format	610 x 90 x 15 mm	Admissible difference in width	± 0.2 mm
Packaging	Pack: 16 elements / 0.88 m ² / 7.23 kg	Squareness of the element	≤ 0.2 %
	Pallet: 48 packs / 42.24 m ² / 367.10 kg	Longitudinal curvature along the element	≤ 0.1 %
Notes	- only suitable for all-over adhesion - cleaning and maintenance: see instruction guide - technical changes reserved	Transverse curvature across the width	≤ 0.2 %
		Height differences of elements	≤ 0.2 mm
		Moisture content at the time of first delivery (5-9%)	6 – 8%
Guarantee (acc. to Parador guarantee conditions)	25 years (domestic area)	Top layer	~ 3.5 mm

Product labelling



EN 14342:2013



The mark of responsible forestry



Classification general product features and surface characteristics

	Test method	Rating / Information
Profile		T & G
Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chair mat
Thermal resistance Suitable for installation over underfloor heating.	EN 12664	0.11 m ² *K/W
E1 HCHO	EN 16516	≤ 0.05 ppm
Slip resistance	EN 13893	μ ≥ 0.35
Reaction to fire	EN 13501-1	D _n s1
Chemical resistance	EN 13442	Category 5
Bond strength / Cross cutting test	ISO 2409	Category 1

Free sorting according to EN 13489

Type of wood (top layer):	Oak
Botanical name / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L., spp / QCXE
Internal abbreviation:	AFP CHEV-EI / N3 / 20221115
Grade:	Nature
Features (upper side of each plank) „Features shall be measured according to EN 1310“	
Sound sapwood	not allowed
Knot (intergrown)	allowed: up to 30mm
Open knots	allowed: up to 15mm
Pinknots	allowed: cluster of knots
Filling	allowed
Cracks / hairline cracks	allowed (no end cracks)
Bark pocket	not allowed
Lightning cracks	allowed
Slope of grain	allowed
Medullary ray	allowed
Discoloration, colour variation	allowed: uniform colours with slight differences
White streaks	not allowed
Pilling sticks marking	not allowed
Biodeterioration (EN 1311)	not allowed

Non-visible parts

All the features without restrictions on size or length permitted provided they do not affect the strength or durability of the soil.

Comment

Maximum 3% of planks are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.

Changed:	OMB	File name:	PA TDS Parkett Trendtime-10 Chevron EI N3 EN 20230901
Date:	01.08.2013	Latest update at:	www.parador.de
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			Page 1 of 1 01.09.2023