PARADOR

Design flooring Vinyl Trendime 5

Product quality		
Formats		914 x 457 x 6,0 mm
Packaging	**Pack:**	5 elements / 2.088 m² / 21.067 kg
	Pallet:	40 packs / 83,540 m² / 882,66 kg

Tolerances (Requirement EN 16511:2023)		
Squareness of the elements (≤ 0.20mm)		≤ 0,15 mm
Determination of Linearity (≤ 0.30 mm/m)		≤ 0,20 mm/m
Flatness concave / convex	**lengthwise (≤ 0.50/≤ 1.0 %)**	≤ 0,30/≤ 0,50 %
	wide (≤ 0.15/≤ 0.20 %)	≤ 0,10/≤ 0,15 %
Surface flushness	**(average ≤ 0.10 mm)**	(average ≤ 0.10 mm)
	(max. ≤ 0.15 mm)	(max. ≤ 0.15 mm)
Opening between installed elements	**(average ≤ 0.15 mm)**	(average ≤ 0,05 mm)
	(max. ≤ 0.20 mm)	(max. ≤ 0.10 mm)

Guarantee (according Parador guarantee conditions)		Notes
Domestic area	Commercial area	- suitable for all-over adhesion (see notes in our advisor)
Lifetime	10 years	- cleaning an maintenance see instructions
		- technical changes reserved

EN 14041:2004/AC:2006

Classification	
Utility class 23 = domestic areas with intensive use	Utility class 33 = commercial areas with intensive use
The design floor meets all requirements of the designated utility class.	

Requirements / properties		Test method	Rating
	Wear layer	ISO 24340	0,55 mm
	Surface Coating		PUR
	Reaction to fire	EN 13501-1	B_{fl}-s1
	Slip resistance	EN 13893 EN 14041	μ ≥ 0,30 DS
	Staining resistance	EN 438-2	Category 1 + 2: level 5, no visible change Category 3: level 4, slight change
	Light fastness	EN ISO 105 – B02	Blue wool scale: Stage ≥ 6
	Resistance to roller castor chairs	EN ISO 4918	Type W, no visible changes
	Thermal resistance Suitable for installation over underfloor heating when using an appropriate moisture barrier.	EN 12667	0,029 m²*K/W
	Moving a furniture leg	EN ISO 16581	No visible damage (foot type 0)
	Indentation-residual	EN ISO 24343-1	≤ 0,10 mm
	Acoustical - Impact noise reduction	EN ISO 10140	17 dB
	Locking strength	ISO 24334	lengthwise ≥ 4 KN/m transversely ≥ 3 KN/m
	Abrasion	ISO 24338, Procedure B	> 5.000 rev.
	Dimensional stability	EN ISO 23999	≤ 0,15 %
	Water resistance	EN 317	waterproof
	Micro scratch resistance	EN 16094	Method A MSR-A1 For mat surfaces (gloss ≤ 7): ≤ 1,5 unit change at 60°
	Slip resistance	EN 16165, Annex B on an inclined plane	Mineral texture: R9
		EN 16165, Annex C pendulum test	PTV (dry / wet) ≥ 36 Low slip potential according to UK Slip resistance group
	Disposal	EAK-Code-number	20 01 39