

	EN	DE	FR	NL	PL	HU	STANDARD	RESULT
	Size	Größe	Format	Afmeting	Wymiar	Méret	EN ISO 24342	See page 3
	Thickness	Gesamtdicke	Épaisseur	Dikte	Grubość catkowita	Vastagság	EN ISO 24346	4,5 mm
	Wear layer	Nutzschichtdicke	Couche d'usure	Slijtlaag	Grubość warstwy użytkowej	Kopóréteg	EN ISO 24340	0,3 mm
	Locking mechanism ¹	Verriegelungssystem ¹	Système d'emboîtement breveté ¹	Kliksysteem ¹	Mechanizm blokujący ¹	Zármechanizmus ¹		2G™ angling installation system ¹
	Surface treatment	Oberflächenbeschichtung	Traitement de surface	PU-coating	Zabezpieczenie powierzchni	Felületkezelés		K-Guard+® PU coating
	Warranty ²	Garantie ²	Garantie ³	Garantie ²	Gwarancja ²	Garancia ²	Commercial	10 years
							Residential	30 years
	Bevelled edge	Abgeschrägte Kante	Chanfrein	V-groef	Fazowanie	Leélezett szél		No
	Mass per unit area	Flächengewicht	Masse surfacique	Gewicht	Waga catkowita	Egységnyi területére jutó tömeg	EN ISO 23997	7784 g/m ²
	Standards	Belagsart	Type de revêtement	Soort vloerbekleding	Rodzaj wykładziny	Szabványok	EN 16511	Pass (multilayer modular floorcovering panels)
	Classification	Klassifizierung	Classification	Classificatie	Klaszifikacja użytkowa	Besorolás	EN ISO 10874 - Commercial	31: Commercial moderate
							EN ISO 10874 - Domestic	23: Domestic heavy
	Reaction to fire	Entflammbarkeit	Réaction au feu	Vuurbestendigheid	Klasa ogniotrwałości	Tűzzel szembeni viselkedés	EN 13501-1	Bfl-s1
	Staining resistance	Farbbeständigkeit	Résistance aux taches	Vlekbestendigheid	Odporność chemiczna	Foltállóság	EN 438-2	Pass (Grade 5)
	Light fastness	Lichtbeständigkeit	Solidité des couleurs à la lumière	Lichtvastheid	Odporność barwy na światło	Fényállóság	EN ISO 105-B02	Pass (≥ 6)
	Abrasion resistance	Abnutzungsbeständigkeit	Résistance à l'abrasion	Krasvastheid	Grupa ścieralności	Kopásállóság	EN 13329 Annex E	Pass (> 1200 cycles)
	Furniture chair leg	Möbelfuß	Pied d'ameublement	Meubelpoot	Nacisk punktowy mebli	Bútorláb	EN 424	Pass (No visible damage)
	Dimensional stability	Maßstabilität	Stabilité dimensionnelle	Dimensionale stabiliteit	Stabilność wymiarowa	Mérettartás	EN 434/EN ISO 23999	Pass (≤ 0,25%)
	Acoustic impact noise reduction	Schalldämmung	Bruit d'impact	Geluidsdemping	Absorpcja akustyczna	Akusztikus hatás – zajcsökkentés	EN ISO 10140-1:2016	ΔLw = 19 dB
	Indentation - residual	Resteindruck	Poinçonnement rémanent	Indrukgevoeligheid	Wgnieciecie resztkowe	Karcolódás – megmaradó	ISO 24343-1	Pass (≤ 0,1 mm)
	Impact resistance	Schlagfestigkeit	Résistance à l'impact	Impactbestendigheid	Odporność na uderzenia	Ütésállóság	EN 13329 Annex F	Pass (≥ 1800 mm)

	EN	DE	FR	NL	PL	HU	STANDARD	RESULT
	Castor chair continuous use	Stuhlrollenbeanspruchung	Usure due aux chaises à roulettes	Bureaustoeittest bij continu gebruik	Oddziaływanie: krzesła na rolkach	Folyamatos görgősszék-használat	EN 425/ISO 4918	Pass (10 000 cycles)
	Thermal resistance	Wärmedurchlässigkeit (Widerstand)	Résistance thermique	Warmteweerstand	Przewodzenie ciepła	Hőállóság	ISO 8302	0,0184 m²K/W
							Underfloor heating	Suitable. Max 27°C
	Slip resistance ³	Rutschfestigkeit ³	Glissance ³	Slipweerstand ³	Właściwości antypoślizgowe ³	Csúszásgátló képesség ³	EN 13893	DS
							DIN 51130	R10
	Adhesive	Klebstoff	Colle	Lijm	Klej	Ragasztó		None; refer to installation instructions
	Environmental	Umwelt	Environnement	Milieu	Środowisko	Környezeti	French VOC regulation (ISO 16000) ⁴	A+
							Eurofins Indoor Air Comfort	Gold
							FloorScore SCS-EC10.3-2014 v4.0	Certified
							ISO 14001 / ISO 9001	Manufactured in certified facilities
	CE / DOP	CE / DOP	CE / DOP	CE / DOP	CE / DOP	CE / DOP	EN 14041	DOP 2020/RURC/EN/01
	Recycling	Recycling	Recyclable	Recyclebaar	Recykling	Újrafeldolgozhatóság		Suitable
	Phthalate free	Phthalatfrei	Sans phtalates	Ftalaatvrij	Nie zawiera ftalanów	Nem tartalmaz ftalátokat		Yes

¹ 2G™ is a patented technology invented by Välinge Innovation AB. The 2G™ word mark and logo are registered trademarks owned by Välinge Innovation AB and any use of such marks is under license.

² Subject to terms, see website.

³ Slip resistance is measured on freestanding ex-factory product. Slip resistance can be affected by many factors, including but not limited to; product installation and underlayment, surface contamination, use, wear and how the product is maintained. Textural variation along the surface of the product can affect nominal values.

⁴ Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).



Technical Datasheet

Rubens - Rigid Core



Plank/Tile	Size (mm)	Size (in)	Box qty (m ²)	Box qty (pieces)	Slip resistance
Plank	1220,0 x 180,0	48,03 x 7,09	3,074	14	R10