PARADOR

Design floor Vinyl flooring for gluing Trendtime 10

Product quality		
Format		488 x 118 x 2.5 mm
Packaging	**Pack:**	30 elements / 1.728 m² / 7.59 kg
	Palette:	132 packs / 228.096 m² / 1,037.88 kg

Tolerances (requirement EN ISO 10582)	
Weight per unit area	4.300 g/m2 ± 5%
Squareness of the elements (≤ 0.25 mm)	≤ 0,10 mm/m
Determination of linearity (≤ 0.35 mm/m)	≤ 0,20 mm/m
Dimensional stability after exposure to heat (≤ 0,15 %)	≤ 0,15 %
Curling after exposure to heat (≤ 1mm)	≤ 1mm

Guarantee (According Parador guarantee conditions)		**Notes**
Domestic area	Commercial area	- only suitable for all-over adhesion - cleaning and maintenance see instructions - technical changes reserved
Lifetime	10 years	

CE
EN 14041:2004/AC:2006

ÉMISSIONS DANS L'AIR INTÉRIEUR A+ A+ A B C

CERTIFIED SUSTAINABLE PRODUCT QNG READY SENTINEL HOLDING INSTITUT

THIRD-PARTY VERIFIED EPD ISO 14025 and EN 15804 Institut Bauen und Umwelt e.V.

Classification	
Utility class 23 = domestic areas with intensive use	Utility class 33 = commercial areas with intensive use
The design floor meets all requirements of the designated utility class.	

Requirements / properties		**Test method**	**Rating**
	Wear layer	EN ISO 24340	0,55 mm
	Surface Coating		PUR
Bfl-s1	Reaction to fire	EN 13501-1	B_{fl} s1
DS	Slip resistance	EN 13893 EN 14041	μ ≥ 0,30 DS
	Staining resistance	ISO 26987	Index 0, Not affected
	Light fastness	EN ISO 105 – B02	Blue wool scale: Stage ≥ 6
	Resistance to roller castor chairs	ISO 4918	Type W, no visible changes
	Thermal resistance Suitable for installation over underfloor heating	EN 12664	0,012 m²*K/W
	Moving a furniture leg	EN 424	No visible changes
	Indentation-residual	EN ISO 24343-1	≤ 0,10 mm
	Water resistance	EN 317	waterproof
	Slip resistance	EN 16165, Annex B on an inclined plane	Matt finished texture: R10
		EN 16165, Annex C pendulum test	PTV (dry / wet - slider 96) ≥ 40 PTV ≥ 36 = Low slip potential according to UK Slip potential group
	Disposal	EAK-Code-number	20 01 39